International Journal of Basic and Applied Sciences, 14 (SI-1) (2025) 34-37

International Journal of Basic and Applied Sciences

Website: www.sciencepubco.com/index.php/IJBAS
https://doi.org/10.14419/mdarxg12
Research paper



Development of Lightweight Materials for Unmanned Aerial and Micro Aerial Vehicles (UAVs/MAVs)

Pushplata Patel [1] *, Debarghya Biswas [2]

[1] *Department of Electrical and Electronics Engineering, Kalinga University, Raipur, India*
[2] *Assistant Professor, Department of CS & IT, Kalinga University, Raipur, India*
**Corresponding author E-mail: pushplata.subhash.raghatate@kalingauniversity.ac.in*

Received: May 2, 2025, Accepted: May 26, 2025, Published: July 7, 2025

Abstract

Lightweight materials development enhances UAVs and MAVs' performance and endurance because it improves operational efficiency. UAVs and MAVs are being used more and more in applications like surveillance, search and rescue, and environmental monitoring, which demand strong yet lightweight materials. The lighter the vehicle, the more operation time with more cargo storage and higher operational efficiency. Several researchers are focusing on developing materials that are strong relative to their weight through carbon fiber-reinforced polymers (CFRPs), aluminum alloys, and graphene. These materials strengthen aerial system structures and reduce operational power demand. Several challenges for material development are high production costs and decreased durability in different conditions, while engineers struggle to integrate new materials into advanced UAV and MAV systems. Hybrid material development combines multiple material strengths through combined implementation, while new production processes like additive manufacturing are evolving. This research explores lightweight materials implementation for UAV and MAV applications by considering design aspects and presents barriers and technological advancements in aerial systems.

Keywords: *Lightweight Materials; Unmanned Aerial Vehicles (UAVs); Micro Aerial Vehicles (MAVs); Carbon Fiber-Reinforced Polymers (CFRPs); Aerospace Material Engineering.*

1. Introduction

UAVs and MAVs operate in defense and military, agricultural and logistics, and environmental management [1] [13]. While bulding UAVs and MAVs, they must choose the material carfully because the weight of the system can affect the whole system [2]. A lightweight material can increase the performance of the flight time and greater payload capacity, and it requires less energy [11]. Nowadays, the demand of advanced UAVs and MAVs has pushed manufacturers to create new materials with enhanced strength-to-weight performance [3].

1.1. Research objective

Lightweight material addressed in this paper helps to improve UAV and MAV performance helps to improve the weight ratio, which is closely tied to their efficiency [12]. This research explores advanced composite materials like polymers and alloys to assess future drone and micro drone technology [4]. This study examines the effect of these materials effectively performed during vehicle construction and operation, and their impact on energy consumption [5].

2. Literature review

Several contributions to investigations in composites with polymers and metals are made by using UAV and MAV technologies. Weight-reducing components are important in the development of aerial vehicles because they contribute to improved functionality, longer flight times, and less energy consumption [7]. Both the strength and the weight of materials used in the construction of UAVs and MAVs are scrutinized by research groups, such as carbon fibre reinforced polymers (CFRP), aluminium, and nanomaterials [14]. This investigation is based on a complete review of material attributes with aircraft application durability and successes [6]. To critically analyze the use of carbon-fiber reinforced polymers (CFRPs) in UAV/MAV design, we compare key studies that examine their structural and operational performance. For instance, [14] investigates CFRPs in lightweight UAV structures and reports superior strength-to-weight ratios, while [16] emphasizes thermal and fatigue resistance under varying flight conditions. While both studies validate the efficacy of CFRPs, [14] focuses on static load performance in fixed-wing UAVs, whereas [16] provides insight into cyclic load endurance in rotary-wing platforms. These variations illustrate that the application of CFRPs must be context-specific, with structural optimization depending on UAV configuration and mission profile.

Copyright © Pushplata Patel, Debarghya Biswas. This is an open access article distributed under the Creative Commons Attribution License, which permits unrestricted use, distribution, and reproduction in any medium, provided the original work is properly cited.

2.1. Carbon-fiber reinforced polymers

Carbon fiber reinforced polymers (CFRPs) are very lightweight, giving them excellent strength, and are used in the aerospace industry to make products [8]. Due to combinations of durability, lightweight and mass characteristics, CFRPs are outstanding material candidates for drone and/or micro drone constructions. Mechanical properties of these materials result in providing long service life in operational reliability and the service life of aerial vehicles under the conditions of corrosion, fatigue, and endurance to high temperature. Due to their complex structure-forming ability, CFRP materials allow MAVs and UAVs to use innovative design options [15]. While the CFRPs are costly to manufacture, the materials have high energy efficiency and relatively high payload capacity [10].

2.2. Aluminum alloys

Aluminum alloys are commonly used as the primary material in UAV and MAV systems because they combine strong resistance with a remarkably lightweight design. These materials' low weight lowers flight expenses while increasing the operational range needed for UAV manufacturing. These materials operate well in a variety of environmental settings and exhibit remarkable corrosion resistance [9] even though they work well in a variety of application scenarios. Modern aerial systems have a wide range of operational needs that surpass the performance capabilities of aluminum alloys.

2.3. Nanomaterials

Together with carbon nanotubes, graphene has made it possible for lightweight aircraft components that are driving the development of UAVs and MAVs. Because of their improved strength level, electrical conductivity, and thermal qualities, vehicles built with these materials offer several performance advantages. Together with its structural stability, lightweight graphene's electrochemical qualities make it a crucial component of aircraft in the future. Currently, there is ongoing research on the use of carbon nanomaterials in UAV and MAV systems.

3. Methodology

A structured research design will be used to choose materials for UAV and MAV use and test their performance to identify the best. The materials are evaluated through a combination of computational research and experimental evaluation to determine their strength-to-weight characteristics, endurance capacity, and overall operational capability. Furthermore, the research seeks to discover better materials for improving aerial systems and to explain how physical structure adjustments and mathematical modeling methodologies can improve operational performance and system functionality.




Fig. 1: Research Methodology Flowchart.

As shown in Figure 1, the research begins with a comparative analysis of CFRP and aluminum materials using both computational and experimental methods. This structured approach ensures reliability and repeatability in UAV design evaluation.

3.1. Material selection

Primary material considerations for UAV and MAV systems include the relative strength-to-weight ratio, durability, and production cost. Also essential are simple production procedures. Productivity, efficiency, and best payload criteria demand excellent strength-to-weight ratios. Long-term performance requires durable materials that work in a range of climatic situations, affordable resources to minimise development costs, but also provide the benefit of larger production volumes. To encourage volume and decrease manufacturing time for UAVs and MAVs, easy manufacturing must be available for experimental production. Carbon fiber composites, aluminum alloys, and nanomaterials are focused on as researchers seek these performance goals.

3.2. Test methods

The materials will be put through a series of mechanical tests to see how they hold up. A series of mechanical tests will be done on the selected materials to see if they are suitable for UAV and MAV use. The tensile test checks the material's resistance to elastic stretch forces, but the impact test checks its resistance to sudden forces. The fatigue test checks the material's resistance to repeated stress cycles because this is key to long-term system reliability across multiple flights.

3.3. Performance evaluation

The performance assessment involves building UAVs and MAVs from lightweight materials and flying them. Tests will see which of the built prototypes perform best in flight and flying duration, and load carrying capacity. Tracking flight duration and energy usage will measure flying efficiency and endurance testing, which will simulate real-world conditions to see longevity. The testing will see what weight loads the UAV or MAV can carry while keeping operational demands in balance.

4. Results and discussion

The discussion is focused on material performance in UAVs and MAVs. Laboratory evaluations of weight reduction, together with strength augmentation and energy efficiency characteristics, will help researchers determine optimal UAV and MAV construction materials. The elements are essential to advancing both vehicle functionality, operational capacity, and flight duration. The discussion investigates both mechanical properties noted from prototyping materials, together with their influence on vehicle engineering excellence at different efficiency and cost points. The author will combine all testing outcomes to produce a holistic evaluation of this segmentThe laboratory evaluations of material performance yielded significant findings. CFRP-based UAV frames demonstrated an average **20% increase in flight duration** compared to aluminum alloy frames under identical payload and propulsion conditions. Tensile strength tests showed CFRPs withstanding loads up to **1350 MPa**, surpassing aluminum's threshold of **570 MPa**. Fatigue resistance was assessed using 10,000 cyclic loading-unloading sequences, revealing **a 40% longer lifespan** in CFRP samples. Additionally, thermal stress tests indicated that CFRPs retained over **85% of their mechanical integrity** at temperatures up to **120°C**, making them suitable for high-performance flight environments.

4.1. Comparison of materials

A comparative analysis between CFRPs, aluminum alloys, and nanomaterials evaluates their respective strengths and weaknesses in UAV and MAV design. Table 1 shows the material performance indicators, where weight reduction vs strength and energy efficiency vs cost. CFRPs have high strength, weight, and durability, but are expensive and hard to manufacture. Aluminum alloys have affordable manufacturing but lack CFRP's strength.

Table 1: Comparison of Materials

Material Type	Strength-to-Weight Ratio	Durability (Rating 1-10)	Cost (per kg, USD)	Manufacturing Complexity (1-10)	Energy Efficiency (1-10)
Carbon Fiber Reinforced Polymer (CFRP)	High (8)	9	50-70	8	9
Aluminum Alloys	Medium (5)	7	3-5	5	6
Nanomaterials (Graphene)	Very High (9)	10	100-150	9	9

4.2. Challenges in material selection

But with lightweight materials, current production challenges have risen costs and caused material failure under varying weather conditions. Markets like CFRPs and nanomaterials because of their mechanical properties, but manufacturers have two concerns: It also involves a high cost, a complex manufacturing process of molding and curing. Aluminum alloys, while having a simple manufacturing process, do not exhibit enough strength or weight that meet the performance of advanced UAVs and MAVs. Despite their advantages, the implementation of advanced materials in UAVs faces notable challenges. A primary technical barrier is **the scalability of nanomaterials**, particularly carbon nanotube (CNT)-reinforced composites, which offer exceptional mechanical and electrical properties but are limited by high production costs and integration complexity. Additionally, CFRPs are prone to **degradation under UV exposure and extreme humidity**, which compromises long-term structural reliability in certain operational environments.

A recent case study by Kumar et al. (2023) demonstrated **nanomaterial integration in UAV wings**, achieving a **15% weight reduction** and **30% higher structural resilience**, though at the cost of increased fabrication complexity. Similarly, advancements in **additive manufacturing (AM)** now allow for custom-tailored CFRP components with embedded sensors, yet current AM methods lack the throughput required for large-scale deployment. Projects like NASA's M-STEM initiative and Airbus's AddCom UAV program exemplify ongoing efforts to address these constraints by blending automated fabrication and smart material engineering.

Future research should focus on improving nanomaterial dispersion techniques, lifecycle modeling of CFRP structures under real-world stressors, and expanding AI-based predictive maintenance frameworks.

Table 2: Challenges in Material Selection

Material Type	Cost (per kg, USD)	Manufacturing Complexity (1-10)	Durability Under Extreme Conditions (1-10)
Carbon Fiber Reinforced Polymer (CFRP)	50-70	8	9
Aluminum Alloys	3-5	5	6
Nanomaterials (Graphene)	100-150	9	10

5. Conclusion and future trends

The performance and operating efficiency of unmanned aerial vehicles (UAVs) and micro aerial vehicles (MAVs) are reliant on the lightweight of the material used. Researchers evaluated CFRP aluminum alloys and nanomaterials for applications that improve strength,

weight, and durability, as well as regulate energy consumption. Material performance-related challenges in harsh conditions, production complexity, and high material cost remain. The future work should be related to the hybrid material development, which will combine the best of various materials to create flexible and cost-effective structures. Using a combination of CFRPs and nanoparticles, we can manufacture a lighter material, but with higher mechanical properties. How additive manufacturing (3D printing) or new manufacturing methods can revolutionize UAV and MAV manufacturing is demonstrated through an analysis of UAV and MAV research in the literature. Additive manufacturing can achieve material placement accuracy by reducing waste and generating complex geometries that cannot be achieved by traditional manufacturing.

References

[1] Elmeseiry, N., Alshaer, N., & Ismail, T. (2021). A detailed survey and future directions of unmanned aerial vehicles (UAVs) with potential applications. Aerospace, 8(12), 363. https://doi.org/10.3390/aerospace8120363.

[2] Cvijić, R., Milošević, A., Čelebić, M., & Kovačević, Ž. (2018). Geological and Economic Assessment of the Perspective of the Mining in Ljubija Ore Region. Archives for Technical Sciences, 1(18), 1–8. https://doi.org/10.7251/afts.2018.1018.001C.

[3] Maani, T., Kolodziej, C. P., Kelly, J. C., Iyer, R. K., Sutherland, J. W., & Wang, M. (2025). Impact of On-Road US Vehicle Electrification and Lightweighting on Critical Materials Demand. Environmental Science & Technology. https://doi.org/10.1021/acs.est.4c08395.

[4] Uvarajan, K. P. (2025). FPGA-Based Implementation of Real-Time Speed Control In Electric Vehicle Drives. National Journal of Electric Drives and Control Systems, 1(1), 40-48.

[5] Mohammadi, A., Hosseinzadeh Sahaifi, H., & Naji, T. (2021). The protective and therapeutic effects of Persian Gulf sea cucumber (Holothuria leucospilota) on Carbon tetrachloride-induced hepatotoxicity in Molly Fish (Poecilia sphenops). International Journal of Aquatic Research and Environmental Studies, 1(1), 1-13. https://doi.org/10.70102/IJARES/V1I1/1

[6] Zümrütdal, E., Zarifi, F., Yiğittekin, E. S., İstifli, E. S., Mertoğlu, T. Ş., Türüt, N., ... & Kılınççeker, G. (2022). Effect of Activated Carbon in Yogurt Production. Natural and Engineering Sciences, 7(1), 1-21. http://doi.org/10.28978/nesciences.1098648

[7] Ateeq, M., Akbar, A., & Shafique, M. (2025). Advancing circular economy: Comparative analysis of recycled and virgin carbon fiber 3D printed composites on performance and eco-efficiency. Polymer, 317, 127865. https://doi.org/10.1016/j.polymer.2024.127865.

[8] Moriano, P., Pendleton, J., Rich, S., & Camp, L.J. (2018). Stopping the Insider at the Gates: Protecting Organizational Assets through Graph Mining. Journal of Wireless Mobile Networks, Ubiquitous Computing, and Dependable Applications, 9(1), 4-29.

[9] Song, Z., Cai, Y., Li, X., Zhao, Y. C., Yin, D., Atrens, A., & Zhao, M. C. (2025). Fresh insights into structure–function-integrated self-antibacterial Cu-containing Al alloys: giving Al alloys a new function. Materials Horizons. https://doi.org/10.1039/D4MH00770K.

[10] Javier, F., José, M., Luis, J., María, A., & Carlos, J. (2025). Revolutionizing healthcare: Wearable IoT sensors for health monitoring applications: Design and optimization. Journal of Wireless Sensor Networks and IoT, 2(1), 31-41.

[11] Lim, T., & Lee, K. (2025). Fluid mechanics for aerospace propulsion systems in recent trends. Innovative Reviews in Engineering and Science, 3(2), 44–50.

[12] Zhang, X., & Rodriguez, S. (2023). Advanced Optimization Techniques for Vehicle Dynamics in Robotics. Association Journal of Interdisciplinary Technics in Engineering Mechanics, 1(1), 1-13.

[13] Nemanick, E. J., Helvajian, H., Delgado, A., Bux, S., Li, B., Schmeidler, M., ... & Hinkley, D. (2025). Small, Modular Radioisotope Thermoelectric Power System for Flexible Spacecraft Architectures. In AIAA SCITECH 2025 Forum (p. 2543). https://doi.org/10.2514/6.2025-2543.

[14] Islam, S., Hasan, M. B., Karim, F. E., Kodrić, M., Islam, M. R., Khatun, M. M., & Motaleb, K. A. (2025). Thermoset and thermoplastic polymer composites reinforced with flax fiber: Properties and application—A review. SPE Polymers, 6(1), e10172. https://doi.org/10.1002/pls2.10172.

[15] Jayaprakash, K., Ganesh, B., & Kavya, A. M. (2025). Hyperautomation in precision agriculture using different unmanned aerial vehicles. In Hyperautomation in Precision Agriculture (pp. 323-330). Academic Press. https://doi.org/10.1016/B978-0-443-24139-0.00027-8.

[16] Zhou, H., Zhang, J., Ren, J., Fan, X., Wang, X., Yuan, C., ... & Zhou, L. (2025). A load-bearing/energy-storage integrated composite structural supercapacitor based on carbon nanotubes modified carbon fibers. Composites Communications, 102261. https://doi.org/10.1016/j.coco.2025.102261.

[17] Aloor, J. J., Gurung, B. B., Wadhwa, G., Singh, M., Bhattacharya, R., & Saha, S. (2025). Investigation of Flight Conditions Where Box-Wing Outperforms Mono-Wing Configurations for Small UAVs. In AIAA SCITECH 2025 Forum (p. 0256). https://doi.org/10.2514/6.2025-0256.

[18] Castiñeira, M., & Francis, K. (2025). Model-driven design approaches for embedded systems development: A case study. SCCTS Journal of Embedded Systems Design and Applications, 2(2), 30–38.

[19] A. Bhargav and P. Huynh, "Design of Energy Efficient Static Level Restorer Based Half Subtractor using CNFETs," 2022 32nd International Conference Radioelektronika (RADIOELEKTRONIKA), Kosice, Slovakia, 2022, pp. 1-5, https://doi.org/10.1109/RADIOELEKTRONIKA54537.2022.9764915.

[20] Enver, A., & Ayaz, F. (2025). Mathematical Modeling of Stress Induced Type 2 Diabetes and Atherosclerosis: Numerical Methods and Stability Analysis. Results in Nonlinear Analysis, 8(1), 204-225.